

Product Information

S-Bond® 220-50



Recommended Information 2004

Description

S-Bond® 220-50 is a Sn-Ag-Ti based active solder joining a range of metals, light metals and ceramic materials.

Melting Range

- Solidus Temperature: 428° F (221° C)
- Liquidus Temperature: 447° F (232° C)
- Joining Temperature: 482 – 536° F (250 – 280° C)

Physical Properties

- Density: 0.264 lbs/in³ (7.3 g/cc)
- Thermal Coefficient of Expansion from R.T. to 300° F (25 – 150° C):
~19 x 10⁻⁶ / °C
- Electrical Resistivity (ρ): 1.6μ-ohm-m
- Thermal Conductivity:
 - Intrinsic: 48 W/mK

Mechanical Properties

- Tensile Strengths: UTS 0.2%Y.S.
 - 25° C..... 7.8 ksi (53 MPa) 5.6 ksi (38 MPa)
 - 75° C..... 6.2 ksi (42 MPa) 4.7 ksi (32 MPa)
 - 175° C..... 3.9 ksi (26 MPa) 3.4 ksi (23 MPa)
 - 190° C..... 3.9 ksi (26 MPa) 3.0 ksi (20 MPa)
- Joint Strength (R.T.):
 - Aluminum to Aluminum 2.9 – 4.3 ksi (20 – 30 MPa)
 - Steel to Steel 2.9 – 7.5 ksi (20 – 52 MPa)
 - Stainless Steel (Type 304) 2.6 – 3.6 ksi (18 – 25 MPa)
 - Copper to Copper 2.9 – 5.8 ksi (20 – 40 MPa)
 - Aluminum to Steel 4.8 – 6.5 ksi (33 – 45 MPa)
 - Al:SiC to Metals 4.4 – 6.0 ksi (30 – 41 MPa)
 - Glass to Metal 3.5 – 5.1 ksi (24 – 35 MPa)

Joint Sealing Capabilities

- Kovar to Alumina 3.8 x 10⁻⁹ atmospheres / cc sec
- SiC to Invar 5 x 10⁻¹⁰ mbar*L/sec (helium leak rate)
- Silicon and Glass to metals 4.1 x 10⁻⁹ atmospheres / cc sec

Corrosion

- Good atmospheric protection/salt spray resistance is good since Ti passivates alloy. Resistant to Cl in solution.
- Other corrosion data, updates or special requests.... Please call.

Product Information

S-Bond® 220-50



Recommended Information 2004

Description

S-Bond® 220-50 is a Sn-Ag-Ti based active solder joining a range of metals, light metals and ceramic materials.

Melting Range

- Solidus Temperature: 428° F (221° C)
- Liquidus Temperature: 447° F (232° C)
- Joining Temperature: 482 – 536° F (250 – 280° C)

Physical Properties

- Density: 0.264 lbs/in³ (7.3 g/cc)
- Thermal Coefficient of Expansion from R.T. to 300° F (25 – 150° C):
~19 x 10⁻⁶ / °C
- Electrical Resistivity (ρ): 1.6μ-ohm-m
- Thermal Conductivity:
 - Intrinsic: 48 W/mK

Mechanical Properties

- Tensile Strengths: UTS 0.2%Y.S.
 - 25° C..... 7.8 ksi (53 MPa) 5.6 ksi (38 MPa)
 - 75° C..... 6.2 ksi (42 MPa) 4.7 ksi (32 MPa)
 - 175° C..... 3.9 ksi (26 MPa) 3.4 ksi (23 MPa)
 - 190° C..... 3.9 ksi (26 MPa) 3.0 ksi (20 MPa)
- Joint Strength (R.T.):
 - Aluminum to Aluminum 2.9 – 4.3 ksi (20 – 30 MPa)
 - Steel to Steel 2.9 – 7.5 ksi (20 – 52 MPa)
 - Stainless Steel (Type 304) 2.6 – 3.6 ksi (18 – 25 MPa)
 - Copper to Copper 2.9 – 5.8 ksi (20 – 40 MPa)
 - Aluminum to Steel 4.8 – 6.5 ksi (33 – 45 MPa)
 - Al:SiC to Metals 4.4 – 6.0 ksi (30 – 41 MPa)
 - Glass to Metal 3.5 – 5.1 ksi (24 – 35 MPa)

Joint Sealing Capabilities

- Kovar to Alumina 3.8 x 10⁻⁹ atmospheres / cc sec
- SiC to Invar 5 x 10⁻¹⁰ mbar*L/sec (helium leak rate)
- Silicon and Glass to metals 4.1 x 10⁻⁹ atmospheres / cc sec

Corrosion

- Good atmospheric protection/salt spray resistance is good since Ti passivates alloy. Resistant to Cl in solution.
- Other corrosion data, updates or special requests.... Please call.